

DENSOLEN PRIMER HT

Solvent based primer for corrosion protective coating with special butyl rubber(Densolen Tape)

Description: Densolen Primer HT is a solution of butyl rubber and unsaponifiable resins in petroleum spirit. It improves the peel strength of DENSOLEN tapes on the metal surface and supports their corrosion protection performance. The Primer encloses dust and moisture traces and neutralises same. Is suitable for steel and non-ferrous metal surfaces, is compatible with coatings of PE, PP, Epoxy, PU and bitumen/coaltar.

Properties:	Consistency	Liquid
	Colour:	Black
	Smell:	As gasoline
	Density:	Ca. 079 g/cm ³
	Flash point:	-14° (DIN 51 755)
	Ignition temperature:	Ca. +250°C (DIN 51 755)
	Explosive limits in air:	Lower: 1,0 vol% Upper: 6,5 vol%

By heating and fire: The product is flammable. Vapors may form explosive mixtures with air, can be ignited by embers and sparks.

Method for application: All loose material - soil, dust, rust and other contaminants must be removed from pipes and coating. Any moisture and frost is removed by drying or heating. Care should be taken to plastics nowhere heated to more than 60 ° C.

To ensure the best possible adhesion, rub the surfaces with a cloth moistened with benzene or methylated spirits, thereby removing oil and grease.

Densolen Primer HT is stirred thoroughly in the packaging. Primer applied by brush in a thin layer. The use is about 0.25 ltr/m². At large tube can be advantageously employed a roller. Drying is about 15 min. depending on conditions. When the tape imposed should the primer is no longer spill over to the touch, but may well feel slightly sticky. Wounding no later than 4 hours after it is applied.

In order to avoid that the primer is too thick, it should not be left a long time without a lid. Any dilution may be made with benzene. Thorough agitation of the primer is repeated throughout the work.

Storage and handling:	Special precautions:	Storage and use in a well ventilated place and kept away from sources of ignition. Avoid the packaging is open longer. Take precautionary measures against static electricity. Wear gloves and goggles when there is risk of splashing.
------------------------------	----------------------	---

Accidental:	Confine and absorb with sand.
-------------	-------------------------------

Waste treatment:	Waste is collected in sealable containers and delivered to the receiving station.
------------------	---

Unit and package:	Cans 1 liter - Buckets 10 liter - Drums 180 liter
--------------------------	---

DENSOLEN KIT WP - W

Cavity filler to be used in combination with special butyl rubber(Densolen Tape)

Use:	For filling voids, cracks and damaged areas of defective pipeline coatings, to contour the steel surface adjacent to the weld bead on spirally or longitudinally welded pipes, for filling hollows on T-pieces and fittings.		
Description:	Permanently plastic, non curing, manually applied butyl rubber mastic for void filling and compensation of uneven surfaces.		
Properties:	Density:	1,58 g/ml	
	Application temperature:	-10°C to +40°C	
Unit and package:	Densolen Kit W	Densolen Kit W	
	Profile (40x5 mm)	1 kg bars	
	Roll lenght 2 m	10 bars per carton	
	8 rolls per carton		